

508-982

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
9 October 2003 (09.10.2003)

PCT

(10) International Publication Number
WO 03/082779 A1

(51) International Patent Classification⁷: **C07C 2/12**,
29/16, C07B 37/02, C07C 303/02

(21) International Application Number: PCT/US03/09520

(22) International Filing Date: 28 March 2003 (28.03.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/368,874 29 March 2002 (29.03.2002) US

(63) Related by continuation (CON) or continuation-in-part (CIP) to earlier applications:

US	60/368,874 (CON)
Filed on	29 March 2002 (29.03.2002)
US	60/369,232 (CON)
Filed on	29 March 2002 (29.03.2002)
US	60/368,928 (CON)
Filed on	29 March 2002 (29.03.2002)
US	60/368,917 (CON)
Filed on	29 March 2002 (29.03.2002)
US	60/368,864 (CON)
Filed on	29 March 2002 (29.03.2002)

(71) Applicant (for all designated States except US): **EXXON-MOBIL CHEMICAL PATENTS, INC.** [US/US]; A corporation of the State of Delaware, 5200 Bayway Drive, Baytown, TX 77520-5200 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **BEADLE, Stephen, W.** [US/US]; 11014 Jack Kramer Drive, Baton Rouge, LA 70810 (US). **CHENG-GUAJARDO, Cesar, M.** [US/US]; 12378 Fairhaven Drive, Baton Rouge, LA 70815 (US). **DUNCAN, Carolyn, B.** [US/US]; 7312 N. Jefferson Place Circle, Baton Rouge, LA 70809 (US). **TURNER, David, W.** [US/US]; 4520 S. Sherwood Forest, Suite 104-180, Baton Rouge, LA 70816 (US). **SALEH, Ramzi, Y.** [US/US]; 8008 Bluebonnet Road, 416-15, Baton Rouge, LA 70810 (US).

(74) Agents: **MORENO, Louis, N.** et al.; ExxonMobil Chemical Company, Law Technology, P.O.Box 2149, Baytown, TX 77522-2149 (US).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,

GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

— as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

Published:

— with international search report

[Continued on next page]

(54) Title: A PROCESS FOR PREPARING AN OLEFINIC HYDROCARBON MIXTURE

(57) Abstract: In a process for preparing an olefinic hydrocarbon mixture comprising at least 5% by weight of mono-olefin oligomers of the empirical formula; C_nH_{2n} where n greater than or equal to 6, a feedstock comprising n-butene and propylene in a molar ratio of about 1:0.01 to about 1:0.49 is contacted under oligomerization conditions with surface deactivated ZSM-23. The resultant mono-olefin oligomers comprise at least 20 percent by weight of olefins having at least 12 carbon atoms, wherein said olefins having at least 12 carbon atoms have an average of from about 0.8 to about 2.0 C_1-C_3 alkyl branches per carbon chain.

WO 03/082779 A1

WO 03/082779 A1



For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

**A PROCESS FOR PREPARING AN OLEFINIC HYDROCARBON
MIXTURE**

FIELD

[0001] This invention relates to a process for preparing an olefinic hydrocarbon mixture.

BACKGROUND

[0002] Long chain olefins (C_{10+}) are important starting materials in the production of sulfonate surfactants, in which the olefins are used to alkylate aromatic hydrocarbons and the resultant alkyl aromatics are sulfonated to produce alkylaryl sulfonates. In addition, the alcohols of long chain olefins have considerable commercial importance in a variety of applications, including detergents, soaps, surfactants, and freeze point depressants in lubricating oils. In such applications, the degree and the position of the branching along the carbon chain of the olefin is often critical to the properties of the end product. Thus, for example, highly branched olefins tend to produce surfactants with poor biodegradability, whereas substantially linear olefins tend to produce surfactants with poor hard and cold water cleaning properties. In addition, it is found that lightly branched olefins, where the branching is at the odd-numbered positions in the carbon chain, produce surfactants with enhanced biodegradability as compared to similar olefins where the branching is at the even-numbered positions in the carbon chain.

[0003] One potential route for the production of long chain olefins is by the oligomerization of lower (C_2 to C_6) olefins, typically using an acidic catalyst, such as a zeolite. Thus, for example, it is known from U.S. Patent Nos. 3,960,978, 4,150,062; 4,211,640; 4,227,992; and 4,547,613 to oligomerize lower olefins over ZSM-5, but the resultant oligomers are essentially linear.

[0004] U.S. Patent No. 5,026,933 describes a process for producing high molecular weight, slightly branched hydrocarbon oligomers from a lower olefin

feedstock employing a shape selective crystalline silicate catalyst, ZSM-23, which has been surface deactivated. The resultant oligomer mixture comprises at least 20% by weight of olefins having at least 12 carbon atoms and said olefins having at least 12 carbon atoms have an average of from 0.8 to 2.0 methyl branches per carbon chain. The lower olefin feedstock employed is either propylene or n-butene.

[0005] Further investigation of the process described in the '933 patent has now shown that, whereas oligomerization of n-butene produces oligomers in which the majority of the branching appears to be at the odd-numbered positions, such as the 3- and 5-positions, in the carbon chain, oligomerization of propylene produces oligomers in which the majority of the branching appears to be at the even-numbered positions in the carbon chain. Surprisingly, it has also been found that oligomerization of mixtures of n-butene and propylene at molar ratios up to 1:0.49 produces oligomers in which the position of the branching appears to be similar to that obtained with butene alone, i.e., apparently concentrated at the odd-numbered positions in the carbon chain. Since propylene is available in large quantities in a modern integrated oil refinery, this discovery provides an important extension to the applicability of the process of the '933 patent.

SUMMARY

[0006] Accordingly, the invention resides in a first aspect in a process for preparing an olefinic hydrocarbon mixture comprising at least 5 wt%, such as at least 20 wt%, for example at least 85 wt%, of mono-olefin oligomers of the empirical formula:



where n is greater than or equal to 6, said mono-olefin oligomers comprising at least 20 percent by weight of olefins having at least 12 carbon atoms, said olefins having at least 12 carbon atoms having an average of from about 0.8 to about 2.0 C₁-C₃ alkyl branches per carbon chain, said process comprising contacting a feedstock comprising n-butene and propylene in a molar ratio of about 1:0.01 to about 1:0.49, under oligomerization conditions with surface deactivated ZSM-23.

[0007] Conveniently, said feedstock contains n-butene and propylene in a molar ratio of about 1:0.05 to about 1:0.35.

[0008] Conveniently, the ZSM-23 has been surface deactivated with a sterically hindered nitrogenous base, such as 2,4,6-collidine.

[0009] In a second aspect, the invention resides in a process for producing a long chain alcohol mixture comprising contacting at least part of said olefinic hydrocarbon mixture with carbon monoxide and hydrogen under hydroformylation conditions and in the presence of a hydroformylation catalyst.

[0010] In a third aspect, the invention resides in a process for producing an alkylaromatic compound comprising contacting an aromatic compound with at least part of said olefinic hydrocarbon mixture under alkylation conditions and in the presence of an alkylation catalyst.

[0011] In yet a fourth aspect, the invention resides in a process for preparing an alkylaryl sulfonate by sulfonating the alkylaromatic compound produced in accordance with said third aspect of the invention.

DETAILED DESCRIPTION OF THE EMBODIMENTS

[0012] The present invention provides an improved process for producing slightly branched, high molecular weight olefinic hydrocarbons by oligomerizing a lower olefinic hydrocarbon feedstock in the presence of a surface-deactivated ZSM-23 catalyst. The use of such a catalyst allows the use of an olefin feedstock comprising a mixture of n-butene and propylene apparently without significant reduction in the amount of branching at the odd-numbered positions in the carbon chain of the resultant oligomers.

[0013] The hydrocarbon feedstock used in the process of the invention comprises n-butene and propylene in a molar ratio of n-butene to propylene of about 1:0.01 to about 1:0.49 and such as about 1:0.05 to about 1:0.35. In addition, the feedstock can contain low molecular weight, typically C₄-C₆, saturated hydrocarbons, which can act as a heat sink during the exothermic oligomerization process. In general, the feedstock can contain up to 80wt%, or more typically up to 50wt%, of paraffins.

[0014] The oligomerization catalyst used in the process of the invention comprises ZSM-23 which has been surface deactivated, conveniently by treatment with a sterically hindered nitrogenous base, such as a trialkyl pyridine compound, and preferably with 2,4,6-collidine (2,4,6-trimethyl pyridine, gamma-collidine). The surface deactivating compound should have a minimum cross-sectional diameter greater than the effective pore size of the zeolite to be treated; i.e., greater than 5 Angstroms. ZSM-23 and its characteristic X-ray diffraction pattern are described in detail in U.S. Patent No. 4,076,842, the entire contents of which are incorporated herein by reference. In one embodiment, the ZSM-23 employed in the catalyst has an alpha value of about 25 and a crystal size of less than 0.1 micron and is conveniently composited with a binder, such as alumina.

[0015] Suitable oligomerization conditions include a temperature of about 160°C to about 250°C, such as about 190°C to about 230°C, for example about 210°C to about 220°C; a pressure in the range of about 500 psig (3447 kPa (gauge)) to about 1500 psig (10342 kPa (gauge)), such as in the range of about 750 psig (5171 kPa (gauge)) to about 1250 psig (8618 kPa (gauge)), and a feed weight hourly space velocity (WHSV) in the range of about 0.1 hr⁻¹ to about 4.0 hr⁻¹, such as in the range of about 0.2 hr⁻¹ to about 3.0 hr⁻¹, for example in the range of about 1.75 hr⁻¹ to about 2.25 hr⁻¹.

[0016] Where surface deactivation is achieved by treatment with a trialkyl pyridine compound, the feed to the oligomerization process includes additional trialkyl pyridine compound so that the surface properties of the zeolite are maintained during the process. Further details of the oligomerization process can be found in U.S. Patent No. 5,026,933, the entire contents of which are incorporated herein by reference.

[0017] The product of the oligomerization process of the invention is an olefinic hydrocarbon mixture which comprises at least 5 wt%, such as at least 20 wt%, for example at least 85 wt%, of mono-olefin oligomers of the empirical formula:



wherein n is greater than or equal to 6 and wherein said mono-olefin oligomers comprise at least 20 wt%, such as at least 60 wt%, of olefins having at least 12 carbon atoms and said olefins having at least 12 carbon atoms have an average of from about 0.8 to about 2.0, such as about 0.8 to about 1.3, C_1 - C_3 alkyl branches per carbon chain. Conveniently, the olefins having at least 12 carbon atoms contain no branches other than methyl groups and ethyl groups.

[0018] Despite the presence of propylene in the oligomerization feed, it is believed that at least 50% of the C_1 - C_3 alkyl branches in the $C_{12}+$ olefinic product of the present process are located at the odd-numbered positions in the carbon chain.

[0019] By fractionating the olefinic hydrocarbon mixture produced by the oligomerization process of the invention it is possible to produce one or more olefinic fractions, for example a C_{12} olefinic fraction comprising at least 85% by weight of mono-olefins having 12 carbon atoms, said mono-olefins having a straight backbone chain of at least 10 carbon atoms and an average of from about 0.8 to about 2.0 (such as about 0.8 to about 1.3) C_1 - C_3 alkyl branches per carbon chain.

[0020] Part or all of the olefinic hydrocarbon mixture produced by the oligomerization process of the invention is conveniently used in the production of long chain alcohols for application as, for example, detergents, soaps, surfactants, and freeze point depressants in lubricating oils. Typically this is achieved by hydroformylation, that is, reaction with carbon monoxide and hydrogen, according to the Oxo process. Catalysts employed can be cobalt or rhodium which may be modified with phosphine, phosphite, arsine or pyridine ligands, as described in U.S. Pat. Nos. 3,231,621; 3,239,566; 3,239,569; 3,239,570; 3,239,571; 3,420,898; 3,440,291; 3,448,158; 3,448,157; 3,496,203; and 3,496,204; 3,501,515; and 3,527,818, the disclosures of which are incorporated herein by reference.

[0021] Typical hydroformylation reaction conditions include a temperature of about 125°C to about 200°C, a pressure of about 2170 kPa to about 32550 kPa (300 psig to about 4000 psig) and a catalyst to olefin ratio of about 1:5000 to about 1:1. The molar ratio of hydrogen to carbon monoxide is usually

about 0.5 to about 10, such as about 1 to about 2. The hydroformylation reaction typically produces an aldehyde which can then be hydrogenated to generate the required alcohol product.

[0022] The hydroformylation process can be carried out in the presence of an inert solvent, such as a ketone, e.g., acetone, methyl ethyl ketone, methyl isobutyl ketone, acetophenone and cyclohexanone; an aromatic compound, e.g., benzene, toluene and the xylenes; a halogenated aromatic compound, e.g., chlorobenzene and orthodichlorobenzene; a halogenated paraffinic hydrocarbon, e.g., methylene chloride and carbon tetrachloride; a paraffin, e.g., hexane, heptane, methylcyclohexane and isooctane and a nitrile, e.g., such as benzonitrile and acetonitrile.

[0023] The catalyst ligand may be made of tertiary organo phosphines, such as trialkyl phosphines, triamyl phosphine, trihexyl phosphine, dimethyl ethyl phosphine, diamylethyl phosphine, tricyclopentyl (or hexyl) phosphine, diphenyl butyl phosphine, diphenyl benzyl phosphine, triethoxy phosphine, butyl diethoxy phosphine, triphenyl phosphine, dimethyl phenyl phosphine, methyl diphenyl phosphine, dimethyl propyl phosphine, the tritolyl phosphines and the corresponding arsines and stibines. Included as bidentate-type ligands are tetramethyl diphosphinoethane, tetramethyl diphosphinopropane, tetraethyl diphosphinoethane, tetrabutyl diphosphinoethane, dimethyl diethyl diphosphinoethane, tetraphenyl diphosphinoethane, tetra-perfluorophenyl diphosphinoethane, tetraphenyl diphosphinopropane, tetraphenyl diphosphinobutane, dimethyl diphenyl diphosphinoethane, diethyl diphenyl diphosphinopropane and tetratolyl diphosphinoethane.

[0024] Examples of other suitable ligands are the phosphabicyclohydrocarbons, such as 9-hydrocarbyl-9-phosphabicyclononane in which the smallest P-containing ring contains at least 5 carbon atoms. Some examples include 9-aryl-9-phosphabicyclo[4.2.1]nonane, (di)alkyl-9-aryl-9-phosphabicyclo[4.2.1]nonane, 9-alkyl-9-phosphabicyclo[4.2.1]nonane, 9-cycloalkyl-9-phosphabicyclo [4.2.1] nonane, 9-cycloalkenyl-9-

phosphabicyclo[4.2.1]nonane, and their [3.3.1] and [3.2.1] counterparts, as well as their triene counterparts.

[0025] Alternatively, part or all of the olefinic hydrocarbon mixture produced by the oligomerization process of the invention can be used, either alone or in admixture with linear alpha-olefins, as an alkylating agent in a process for the selective alkylation of an aromatic compound (e.g., benzene) with a relatively long chain length alkylating agent to produce substantially linear phenylalkanes. The alkylation process is conducted such that the organic reactants, i.e., the aromatic compound and the olefinic hydrocarbon mixture, are contacted under effective alkylation conditions with a suitable acid catalyst. Suitable aromatic hydrocarbons include benzene, toluene, xylene and naphthalene, with preferred compounds being benzene and toluene.

[0026] In one embodiment, the catalyst is a homogeneous acid catalyst such as a Lewis acid catalyst, for example aluminum chloride. Alternatively, the homogeneous acid catalyst is a Brønsted acid catalyst, such as HF or phosphoric acid. Suitable alkylation conditions with a homogeneous catalyst include a temperature of from about -10°C to about 100°C, a pressure of from about 100 kPa to about 2500 kPa (1.0 to 25 atmospheres), a feed weight hourly space velocity (WHSV) of from about 0.2 hr⁻¹ to about 10 hr⁻¹ and an aromatic compound to olefinic hydrocarbon mixture mole ratio of from about 1:1 to about 15:1. Typical reaction conditions include a temperature of from about 0°C to about 50°C, a pressure of from about 100 kPa to about 300 kPa (1.0 to about 3.0 atmospheres), a feed weight hourly space velocity (WHSV) of from about 0.1 hr⁻¹ to about 0.5 hr⁻¹ and an aromatic compound to olefinic hydrocarbon mixture mole ratio of from about 5:1 to about 10:1. The reactants can be in either the vapor phase or the liquid phase and can be neat, i.e., free from intentional admixture or dilution with other material, or they can be brought into contact with the catalyst composition with the aid of carrier gases or diluents such as, for example, hydrogen or nitrogen.

[0027] In a further embodiment, the alkylation process is conducted in the presence of a heterogeneous catalyst, such as a molecular sieve. Suitable

molecular sieves include mordenite, particularly dealuminized mordenite and other 6-7 Angstrom pore molecular sieves disclosed in U.S. Patent No. 5,026,933, the entire contents of which are incorporated herein by reference.

[0028] In one practical embodiment, the alkylation catalyst comprises a molecular sieve having an X-ray diffraction pattern including d-spacing maxima at 12.4 ± 0.25 , 6.9 ± 0.15 , 3.57 ± 0.07 and 3.42 ± 0.07 Angstrom. The X-ray diffraction data used to characterize said molecular sieve are obtained by standard techniques using the K-alpha doublet of copper as the incident radiation and a diffractometer equipped with a scintillation counter and associated computer as the collection system. Materials having the required X-ray diffraction lines are sometimes referred to as molecular sieves of the MCM-22 family and include MCM-22 (described in U.S. Patent No. 4,954,325), PSH-3 (described in U.S. Patent No. 4,439,409), SSZ-25 (described in U.S. Patent No. 4,826,667), ERB-1 is described in European Patent No. 0293032, ITQ-1 is described in U.S. Patent No. 6,077,498, ITQ-2 is described in International Patent Publication No. WO97/17290, MCM-36 (described in U.S. Patent No. 5,250,277), MCM-49 (described in U.S. Patent No. 5,236,575) and MCM-56 (described in U.S. Patent No. 5,362,697). The entire contents of said patents are incorporated herein by reference.

[0029] The molecular sieve alkylation catalyst can be combined in conventional manner with an oxide binder, such as alumina, such that the final alkylation catalyst contains between about 2 and about 80 wt% sieve.

[0030] With a molecular sieve catalyst, suitable alkylation conditions include a temperature of from about 0°C to about 500°C, a pressure of from about 20 kPa to about 25000 kPa (0.2 to 250 atmospheres), a feed weight hourly space velocity (WHSV) of from about 0.1 hr^{-1} to about 500 hr^{-1} and an aromatic compound to olefinic hydrocarbon mixture mole ratio of from about 1:1 to about 20:1. The WHSV is based upon the weight of the catalyst composition employed, i.e., the total weight of active catalyst (and binder if present). Typical reaction conditions include a temperature within the range of from about 100°C to about 350°C, a pressure of from about 100 kPa to about 2500 kPa (1 to 25 atmospheres), a WHSV of from about 0.5 hr^{-1} to about 100 hr^{-1} and an aromatic compound to

olefinic hydrocarbon mixture mole ratio of from about 4:1 to about 15:1. Again, the reactants can be in either the vapor phase or the liquid phase and can be neat, i.e., free from intentional admixture or dilution with other material, or they can be brought into contact with the zeolite catalyst composition with the aid of carrier gases or diluents such as, for example, hydrogen or nitrogen.

[0031] The alkylation process of the invention produces an alkylaromatic hydrocarbon mixture in which the alkyl side chains are lightly branched and in which most of the aromatic species are located at the 2- or 3- position in the alkyl side chain. The alkylaromatic hydrocarbon mixture is therefore particularly useful as an intermediate in the production of alkylarylsulfonates, which are useful as detergents or surfactants. Processes for sulfonating alkylbenzenes are described in the U.S. Patent No. 4,298,547, the entire contents of which are incorporated herein by reference. More particularly, alkylaromatic hydrocarbons may be converted to alkylarylsulfonates by sulfonation of the aromatic ring with sulfuric acid. The sulfonation reaction is well known in the art and is commonly carried out by contacting the organic compound with sulfuric acid at temperatures of from about -70°C to about +60°C. Detailed descriptions of specific commercial processes abound in the literature. See, for instance, pages 60-62 of INDUSTRIAL CHEMICALS, Third Edition, by W. L. Faith et al, published by John Wiley & Sons, Inc.

CLAIMS

1. A process for preparing an olefinic hydrocarbon mixture comprising at least 5% by weight of mono-olefin oligomers of the empirical formula:



where n is greater than or equal to 6, said mono-olefin oligomers comprising at least 20 percent by weight of olefins having at least 12 carbon atoms, said olefins having at least 12 carbon atoms having an average of from about 0.8 to about 2.0 C₁-C₃ alkyl branches per carbon chain, said process comprising contacting a feedstock comprising n-butene and propylene in a molar ratio of about 1:0.01 to about 1:0.49 under oligomerization conditions with surface deactivated ZSM-23.

2. The process according to claim 1, wherein said feedstock contains n-butene and propylene in a molar ratio of about 1:0.05 to about 1:0.35.

3. The process according to claim 1 or claim 2, wherein said ZSM-23 has been surface deactivated with a sterically hindered nitrogenous base.

4. The process according to claim 3, wherein said sterically hindered nitrogenous base is 2,4,6-collidine.

5. The process according to any preceding claim, wherein said oligomerization conditions include a temperature of about 190 to about 240°C.

6. The process according to any preceding claim, wherein said oligomerization conditions include a temperature of about 200 to about 230°C.

7. The process according to any preceding claim, wherein said oligomerization conditions include a temperature of about 210 to about 220°C.

- 11 -

8. The process according to any preceding claim, wherein said oligomerization conditions comprise a pressure in the range of from about 500 psig (3447 KPa (gauge)) to about 1500 psig (10342 KPa (gauge)).

9. The process according to any preceding claim, wherein said oligomerization conditions comprise a pressure in the range of from about 750 psig (5171 KPa (gauge)) to about 1250 psig (8618 KPa (gauge)).

10. The process according to any preceding claim, wherein said oligomerization conditions comprise a weight hourly space velocity of from about 1.0 hr^{-1} to about 4.0 hr^{-1} .

11. The process according to any preceding claim, wherein said oligomerization conditions comprise a weight hourly space velocity of from about 1.0 hr^{-1} to about 3.0 hr^{-1} .

12. The process according to any preceding claim, wherein said oligomerization conditions comprise a weight hourly space velocity of from about 1.75 hr^{-1} to about 2.25 hr^{-1} .

13. The process according to any preceding claim, wherein said olefins having at least 12 carbon atoms have an average of from about 0.8 to about 1.3 $\text{C}_1\text{-C}_3$ alkyl branches per carbon chain.

14. The process according to any preceding claim, wherein said olefinic hydrocarbon mixture comprises at least 20% by weight of said mono-olefin oligomers.

15. The process according to any preceding claim, wherein said olefinic hydrocarbon mixture comprises at least 85% by weight of said mono-olefin oligomers.

16. A process for producing a long chain alcohol mixture comprising contacting at least part of the olefinic hydrocarbon mixture produced by the process of any preceding claim with carbon monoxide and hydrogen under hydroformylation conditions and in the presence of a hydroformylation catalyst.

17. A process for producing an alkylaromatic compound comprising contacting an aromatic compound with at least part of the olefinic hydrocarbon mixture produced by the process of one of claims 1 to 15 under alkylation conditions and in the presence of an alkylation catalyst.

18. A process for preparing an alkylaryl sulfonate by sulfonating the alkylaromatic compound produced by the process of Claim 17.

INTERNATIONAL SEARCH REPORT

PCT/3/09520

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C07C2/12 C07C29/16 C07B37/02 C07C303/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 026 933 A (BLAIN DAVID A ET AL) 25 June 1991 (1991-06-25) cited in the application claims; examples ---	1-18
A	US 4 855 527 A (PAGE ET AL) 8 August 1989 (1989-08-08) claims -----	1

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

16 June 2003

Date of mailing of the international search report

24/06/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Van Geyt, J

INTERNATIONAL SEARCH REPORT

PCT/93/09520

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5026933	A	25-06-1991	AU 2215288 A	13-04-1989
			CA 1304420 A1	30-06-1992
			DE 3871318 D1	25-06-1992
			EP 0311310 A1	12-04-1989
			JP 1132534 A	25-05-1989
			JP 2562187 B2	11-12-1996
			US 4870038 A	26-09-1989
			US 4855527 A	08-08-1989
<hr/>				
US 4855527	A	08-08-1989	AU 2215288 A	13-04-1989
			CA 1304420 A1	30-06-1992
			DE 3871318 D1	25-06-1992
			EP 0311310 A1	12-04-1989
			JP 1132534 A	25-05-1989
			JP 2562187 B2	11-12-1996
			US 4870038 A	26-09-1989
			US 5026933 A	25-06-1991